

CERAN XM 220



Grease



Extreme-pressure water resistant high temperature **"NEW GENERATION"** calcium sulfonate complex grease.

APPLICATIONS

Multi purpose heavy duty water resistant grease.
Shock loaded applications in industry even in severe demanding environment (water, dust, high temperature).

- **CERAN XM 220** is made of the **NEW GENERATION** calcium sulfonate complex soap designed by TOTAL Lubrifiants. This new soap has enhanced properties in terms of water resistance, load capacity, thermal resistance, anticorrosion properties while keeping a very high level of pumpability and ability to lubricate well in case of high speeds.
- **CERAN XM 220** is suitable for the lubrication of all kinds of components subject to high loads, shocks, working in conditions where the grease is in frequent contact with water (even sea water due to enhanced antirust performances).
- **CERAN XM 220** is suitable for the lubrication of continuous castings and rolling mills in steel plants, bearings in wet and dry (felt rolls) sections of paper mills and all industrial applications under severe conditions (wet, loaded, high temperature, dust,...)
- **CERAN XM 220** is suitable for use in centralized greasing systems.
- Always avoid contamination of the grease by dust and/or dirt when applying. Preferably use a pneumatic pump system.

SPECIFICATIONS

- ISO 6743-9: L-XCFIB1/2
- DIN 51 502: KP1/2R-30

ADVANTAGES

True multi purpose.
Shock loads.
Water resistant.
Anti corrosion.

NEW GENERATION allowing use in high speed applications.

No harmful substances.

- The **NEW GENERATION** of calcium sulfonate complex soap developed by TOTAL Lubrifiants allows **CERAN XM 220** to work well in bearings even if rotation speeds are high. **CERAN XM 220** presents outstanding performances even at high nDm where the **NEW GENERATION** keeps all benefits in terms of corrosion protection, bearings lifetime, high loads and thermal resistance.
- Excellent anti-oxidation and anti-corrosion properties thanks to the excellent behaviour of the calcium sulfonates, also in the presence of sea water.
- The **NEW GENERATION** of calcium sulfonate complex soap allows to keep outstanding **CERAN XM 220** performances even in case of high speed applications where normally polyurea or lithium complex greases are requested.
- **CERAN XM 220** does not contain lead, or other heavy metals considered harmful to human health and the environment.

TOTAL LUBRIFIANTS
INDUSTRIE
18-02-2014 (supersedes 14-12-2010)
CERAN XM 220
1/2



This lubricant used as recommended and for the application for which it has been designed does not present any particular risk.
A material safety data sheet conforming to the regulations in use in the E.C. is obtainable via your commercial adviser www.quick-fds.com.

**TOTAL**

TYPICAL CHARACTERISTICS	METHODS	UNITS	CERAN XM 220 (typical values)
Soap/thickener NLGI grade Color Appearance Operating temperature range Kinematic viscosity of the base oil at 40°C	ASTM D 217/DIN 51 818 Visual Visual ASTM D 445/DIN 51 562-1/ISO 3104/ IP71	- - - °C mm ² /s (cSt)	Calcium sulfonate 1-2 Brown Smooth - 30 to 180 220
<i>Mechanical stability</i>			
Penetration at 25°C Penetration after 100 000 strokes Shell Roller 100 hours at 80°C Shell Roller 100 hours at 80°C + 10% water	ASTM D 217/DIN 51 818 ISO 2137 ASTM D 1831 mod ASTM D 1831 mod	0.1 mm 0.1 mm 0.1 mm 0.1 mm	280-310 +11 -8 -12
<i>Thermal stability</i>			
Dropping point Oil release 50 hours, 100 °C Oil release 168 hours, 40°C Oxidation stability at 99°C +-0.5°C Pressure drop after 100 hours Pressure drop after 500 hours	IP 396 ASTM D 6184 NF T 60-191 ASTM D 942	°C % % Psi Psi	> 300 1.4 0.9 4 13.5
<i>Antirust properties</i>			
EMCOR, distilled water EMCOR, synthetic sea water Copper corrosion, 24 hours at 100°C	ISO 11007 ISO 11007 ASTM D 4048	Rating Rating Rating	0-0 0-0 1b
<i>Antiwear and EP properties</i>			
Four ball wear (scar diameter) Four ball weld load	ASTM D2266 ASTM D2596	mm kgf	0.37 500
<i>Cold properties</i>			
Penetration at -20°C Flow pressure at -20°C Flow pressure at 1400 mbar Torque at -20°C Starting torque After 1 hour	ISO 13737 DIN 51 805 DIN 51 805 ASTM D 1478	0.1 mm mbar °C g.cm g.cm	160 560 -30 2600 460

Above characteristics are mean values given as an information.